



STAMINA

Property	Standard	Unit	Result
----------	----------	------	--------

DESCRIPTION

Surface	X PUR scuff-resistant surface		
Backing	Combined closed cell foam system		
Thickness	EN ISO 24346	mm	2,0
Top layer	EN ISO 24340	mm	0,7
Weight	EN ISO 23997	g/m ²	2800
Width	EN ISO 24341	m	2
Standard roll length	EN ISO 24341	m	20 ± 10%

CLASSIFICATION

Product specification	EN 649 Vinyl floor covering for indoor sport purposes Meets the requirements of EN 14904 on sub-construction		
Thermal resistance	-	m ² K/W	0,01
Reaction to fire	EN 13501	-	C _{fl} -s1
Formaldehyde emission	-	-	No formaldehyde
Pentachlorophenol	-	-	No pentachlorophenol

SPORT PROPERTIES

Friction	PrEN 14903	-	0,4-0,6
Ball rebound	EN 12235	%	> 90
Specular gloss	EN 2813	%	< 30

TECHNICAL CHARACTERISTICS

Dimensional stability	EN ISO 23999	%	± 0,2
Indentation resistance	EN 1516	mm	0,23
Resistance to rolling load	EN 1569	N	1500
Colour fastness	ISO 105 B02	-	6
Chemical resistance	EN ISO 26987	-	no change
Abrasion resistance	EN ISO 5470-1	mg/1000cycles	< 250


OTHERS



3338



6170



7483



2519

Limited warranty



Antimicrobial treatment



Cleanability



No periodic renewal needed; Solvent and heavy metal free

Environmental attributes



GRABOPLAST Floor Covering Manufacturers Ltd.

H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100

mail@graboplast.hu www.graboplast.hu